

	Ln6	B2d
Uniclass Pr_25_71_29_76		



# Monarflex<sup>®</sup> Super T Plus

## TECHNICAL DATA SHEET

Upper Layer	Coated Co-polymer LDPE
Type of Reinforcement	9 mm x 12 mm 1670 dtex PET grid
Lower Layer	Blown Co-polymer LDPE
Eyelet /Structural Type	Rubber eyelet welded to sheet
Colour	Clear (Green in 2m x 45 m size only)

Characteristic	Test method	Value or statement	Tolerance	Units
Length	EN 1848-2	36; 40; 45	±1 %	m
Width	EN 1848-2	2.0; 2.25; 3.0; 4.0	-0.5 / +1.5 %	m
Film thickness	EN 1849-2	0.2	±5 %	mm
Effective thickness	EN 1849-2	0.71	-0.5 / +1.5 %	mm
Membrane mass per unit area	EN 1849-2	258	-5 / +10 %	g·m <sup>-2</sup>
Water tightness	EN 1928 (B)	Class W1	-	-
Reaction to fire	EN 13501-1	Class F	-	-
Tensile strength (MD)	EN 12311-2	>630	-	N/50 mm
Tensile strength (TD)	EN 12311-2	>630	-	N/50 mm
Elongation (MD)	EN 12311-2	>10	-	%
Elongation (TD)	EN 12311-2	>10	-	%
Flexibility at low temperature	EN 1109	≤ -20	-	°C
Tear Resistance	ASTM	≥ 200	-	N
Eyelet Pull Out	BS 7955	≥ 800	-	N
Impact Test	BS7955, Annex A	Conforms	-	-
Puncture Test	BS7955, Annex B	Conforms	-	-
Light Transmission	Monarflex Int. Test	>75	-	%

NPD =No Performance Determined. MD = Machine Direction. TD =Transverse Direction.

Roll Size	Roll Area	Eyelet Rows	Sheet Mass per Unit Area	(Gross) Roll Weight
2.0 m x 45 m	90 m <sup>2</sup>	3	270 g·m <sup>-2</sup>	25 kg
2.25 m x 40 m	90 m <sup>2</sup>	4	274 g·m <sup>-2</sup>	25.5 kg
3.0 m x 45 m	135 m <sup>2</sup>	4	274 g·m <sup>-2</sup>	37.8 kg
4.0 m x 36 m	144 m <sup>2</sup>	6	276 g·m <sup>-2</sup>	40.5 kg

### Description of Product

Monarflex Super T Plus is a three-layer weather barrier consisting a monofilament reinforcing grid with films of special highly weather resistant copolymer low density polyethylene (LDPE) laminated on both sides to form a monolithic membrane. Strong durable rubber fixing eyelets are machine stamped during manufacture in a pre-set repeating pattern.

### Type of Application

Monarflex Super T Plus is intended for use as a high-performance scaffold protection sheet and is suitable for all types of long-term projects exceeding 12 months.

### Compatibility

The material is compatible with all materials normally used in its application. There are no harmful side effects associated with this material.

### Storage and Delivery

Rolls are delivered on pallets, individually wrapped with PE film. These materials should, when removed from pallets, be stored on side, under cover and on a flat, level surface, and protected from mechanical damage and heat sources. During storage exposure to direct sunlight is to be avoided.

### Glossary of Terms

"Membrane" comprises the film and reinforcing grid laminate.  
"Sheet" comprises the membrane including eyelets/reinforcing bands.  
"Gross roll weight" is scaffold sheet plus packaging and cardboard core.

Factory Ref: S0001-01-101

NOTE: This information is given in good faith being based on the latest knowledge known to Icopal Limited. Whilst every effort has been made to ensure the contents of the publication are current while going to press, customers are advised that products, techniques and Codes of Practice are under constant review and liable to change without notice.